

THE FENDER BCS GROUP OF COMPANIES

www.fenderbcs.co.uk

Supa-Fix P

HIGH STRENGTH POLYESTER GROUT FOR ANCHORING & FIXING

PRODUCT FEATURES

Supa-Fix P is a high strength, fast curing polyester resin anchoring grout.

The material consists of a filled polyester resin blend and an organic peroxide catalyst.

Supa-Fix P contains blended fine aggregates and thixotropic additives and is suitable for pumping into horizontal or overhead holes.

Supa-Fix P can be used for the permanent installation of reinforcement doweling and starter bars, handrails, safety fences, wall ties, railway tracks and ground anchors. The product can be used for fixing into concrete, concrete block, brickwork, aerated block and stone.

The product will cure under damp conditions and is resistant to immersion underwater. The cured material also has excellent adhesion, good chemical resistance and negligible shrinkage.

MATERIALS SUPPLIED

1, 2.5 and 10 litre pack size

STORAGE

Protect from frost and away from direct sunlight. Store under dry cool warehouse conditions at a temperature between 10°C and 25°C.

SHELF LIFE

18 months in unopened containers and stored under good conditions.

PREPARATION

Holes should be drilled using rotary percussive drilling techniques. If diamond drilling is used, holes should be scabbled or under-reamed. If these precautions are not taken the smooth finish obtained from diamond drilling can lead to reduced pull-out strengths. Pre-cast holes should be of dovetail configuration and have roughened sides.

After drilling, holes should be brushed and blown out twice, to remove all drilling debris. Bars and bolts should be degreased and any mill scale or rust removed.

MIXING

Supa-Fix P comprises two components, a resin BASE and a catalyst FILLER which are supplied pre-weighed in the correct proportions.

When required for application, the two components should be mixed well, preferably using a mechanical stirrer until a uniform consistency is obtained.

TECHNICAL INFORMATION

Colour	Light Grey
Density gm/cc	1.9
Pot Life	@ 10 °C @ 20 °C 45 mins 20 mins
Compressive Strength @ 20 °C (N/mm ²) (BS6319 Part 2:1983)	1 Hour 3 Hours 24 Hours 63 81 101
Tensile Strength @ 20 °C (N/mm ²) (BS6319 Part 7:1985)	7 Days 18
Flexural Strength @ 20 °C (N/mm ²) (BS6319 Part 3:1990)	28
Application Temperature Range (°C)	0 to 30

Typical Tensile Pull-out Strengths to (BS5080 Part 1: 1974)

Stud Size (mm)	Hole Diameter (mm)	Typical Embedment Depth (mm)	Tensile Failure Load (kN)	Shear Failure Load (kN)
10	14	75	31.9	23
12	16	100	52.8	31
16	20	125	83.7	63.1
20	25	150	117.6	85.4

APPLICATION

The mixed grout should be poured or pumped steadily into the prepared holes well within the gel time. It should be injected to the bottom of the hole to avoid air entrapment. The bar or bolt should then be inserted into the hole to the required depth using a twisting motion. This will assist in ensuring a complete bond.

The assembled bar should be left undisturbed while the grout hardens.

Our expertise is fitting all the pieces together

Fender Steel

Head Office
20 Midland Road
Scunthorpe
North Lincolnshire
DN16 1DQ
Tel: 01724 840609
Fax: 01724 281902

BCS Products

Caenby Corner
Industrial Estate
Hemswell Cliff
Nr. Gainsborough
Lincolnshire DN21 5TU
Tel: 01427 668187
Fax: 01427 668012

Fender Steel

Unit 16A
Enterprise Park,
Bergon Way
Sutton Fields Ind. Est.,
Hull HU7 0YG
Tel: 01482 820620
Fax: 01482 820621

Fender Steel


Unit A5
Astra Park
Parkside Lane
Leeds LS11 5SZ
Tel: 0113 270 4555
Fax: 0113 270 4666

Fender Steel

5 Crofton Court
Portrack Lane
Stockton-on-Tees
Cleveland TS18 2QR
Tel: 01642 603123
Fax: 01642 674892

Fender Steel

5a Freezemoor Road
Houghton le Spring
Sunderland
Tyne & Wear DH4 7BH
Tel: 0191 512 6749
Fax: 0191 584 6547



THE FENDER BCS GROUP OF COMPANIES

www.fenderbcs.co.uk

Supa-Fix P

HIGH STRENGTH POLYESTER GROUT FOR ANCHORING & FIXING

Approximate Volume of Supa-Fix P required (ml) per 100mm of bond length (No allowance made for wastage)

Hole Diameter (mm)	Bolt Diameter					
	12	16	20	25	32	38
20	20					
25	38	29	18			
32	70	60	49	31		
38		94	82	64	33	
45			128	110	79	63
51				155	123	91

GENERAL INFORMATION

The strength of the cured Supa-Fix P permits the assembly of anchors capable of high loadings. The ultimate load will be governed by:-

Strength of substrate
Length of resin bond to bar
Type and dimensions of bar
Anchor separation
Hole Preparation

The specified pullout strengths and safe working loads were obtained on single fixings with spacing of at least twice the embedment depth. In situations with reduced spacing or where fixings are close to edges, appropriate reductions in the safe working load should be made.

CLEANING

Clean uncured material with QUICKMAST SOLVENT. Cured material can only be removed mechanically.

HEALTH AND SAFETY

Consult the appropriate Material Safety Data Sheet prior to using Supa-Fix P.

GENERAL GUIDANCE

This data sheet is for general guidance purposes only and may contain information that is inappropriate for certain conditions of use. Accordingly, all recommendations and suggestions are made without guarantee. Further information is available from our Technical Department.

Our expertise is fitting all the pieces together

Fender Steel

Head Office
20 Midland Road
Scunthorpe
North Lincolnshire
DN16 1DQ
Tel: 01724 840609
Fax: 01724 281902

BCS Products

Caenby Corner
Industrial Estate
Hemswell Cliff
Nr. Gainsborough
Lincolnshire DN21 5TU
Tel: 01427 668187
Fax: 01427 668012

Fender Steel

Unit 16A
Enterprise Park,
Bergon Way
Sutton Fields Ind. Est.,
Hull HU7 0YG
Tel: 01482 820620
Fax: 01482 820621

Fender Steel

Unit A5
Astra Park
Parkside Lane
Leeds LS11 5SZ
Tel: 0113 270 4555
Fax: 0113 270 4666

Fender Steel

5 Crofton Court
Portrack Lane
Stockton-on-Tees
Cleveland TS18 2QR
Tel: 01642 603123
Fax: 01642 674892

Fender Steel

5a Freezemoor Road
Houghton le Spring
Sunderland
Tyne & Wear DH4 7BH
Tel: 0191 512 6749
Fax: 0191 584 6547